



## Dimension board

|                            |                    |
|----------------------------|--------------------|
| <b>LENGTH</b>              | 2200 mm            |
| <b>WIDTH</b>               | 180 mm             |
| <b>TOTAL THICKNESS</b>     | 14.0 mm            |
| <b>THICKNESS TOP LAYER</b> | 3 mm               |
| <b>LAYER CONTENTS</b>      | Min 3 Pl x 2200 mm |

## Dimension pack

|                           |                     |
|---------------------------|---------------------|
| <b>PACK LENGTH</b>        | 2250 mm             |
| <b>PACK WIDTH</b>         | 185 mm              |
| <b>PACK THICKNESS</b>     | 84 mm               |
| <b>PACK WEIGHT</b>        | 23 kg               |
| <b>LAYERS/BOX</b>         | 6                   |
| <b>M<sup>2</sup>/PACK</b> | 2.38 m <sup>2</sup> |

## Dimension pallet

|                             |                       |
|-----------------------------|-----------------------|
| <b>PALLET LENGTH</b>        | 2250 mm               |
| <b>PALLET WIDTH</b>         | 95 mm                 |
| <b>PALLET HEIGHT</b>        | 1100 mm               |
| <b>PALLET WEIGHT</b>        | 1280 kg               |
| <b>PACKS/PALLET</b>         | 55                    |
| <b>M<sup>2</sup>/PALLET</b> | 130.90 m <sup>2</sup> |

**CHARACTERISTICS**

## Top layer

|                            |                            |
|----------------------------|----------------------------|
| <b>WOOD SPECIES</b>        | Oak                        |
| <b>LATIN NAME</b>          | Quercus Robur              |
| <b>GRADE</b>               | ABCD                       |
| <b>CONSTRUCTION</b>        | 2-layer                    |
| <b>THICKNESS TOP LAYER</b> | 3 mm                       |
| <b>PATTERN</b>             | 1 strip                    |
| <b>CUTTING METHOD</b>      | Zaagfineer                 |
| <b>BEVEL</b>               | Bevel 2 long sides 0,75 mm |
| <b>FINISH</b>              | Hardwax oil                |
| <b>SURFACE STRUCTURE</b>   | Smooth                     |

## Composition of the support

|                                |                      |
|--------------------------------|----------------------|
| <b>SUPPORT TYPE</b>            | MPX                  |
| <b>WOOD SPECIES SUPPORT</b>    | Mixed Light Hardwood |
| <b>TOTAL THICKNESS SUPPORT</b> | 11 mm                |
| <b>ADHESION</b>                | Kruiselings          |

## Installation

|                   |  |                           |
|-------------------|--|---------------------------|
| <b>SYSTEM</b>     | <b>APPLICATIONS</b>  | <b>UNDERFLOOR HEATING</b> |
| Tongue and groove | Light household use.<br>Moderate commercial use.<br>Normal commercial use.<br>Normal household use.<br>Intensive commercial use. | Yes                       |
|                   |  | <b>RE-SANDABLE</b>        |
|                   |  | Yes                       |

## TECHNICAL SPECIFICATIONS

|                       | Norm                | Result                 |
|-----------------------|---------------------|------------------------|
| REACTION TO FIRE      | EN 13501-1          | Dfl-S1                 |
| FORMALDEHYDE EMISSION | EN 717-1            | E1                     |
| PCP                   | CEN/TR 14823        | ≤ 5ppm                 |
| THERMAL CONDUCTIVITY  | EN 12667 / ISO 8302 | 0,11m <sup>2</sup> k/w |
| BIOLOGICAL DURABILITY | EN 335              | Class 1                |
| BREAKING STRENGTH     | EN 1533             | Pass                   |
| SLIPPERINESS          | EN 15676            | Pass                   |
| MOISTURE CONTENT      | EN 13183-1          | 7% (+/-2%)             |

## CERTIFICATION



EN 14342

