



### Dimension board

|                            |         |
|----------------------------|---------|
| <b>LENGTH</b>              | 520 mm  |
| <b>WIDTH</b>               | 90 mm   |
| <b>TOTAL THICKNESS</b>     | 15.0 mm |
| <b>THICKNESS TOP LAYER</b> | 4 mm    |

### Dimension pack

|                           |                     |
|---------------------------|---------------------|
| <b>PACK LENGTH</b>        | 590 mm              |
| <b>PACK WIDTH</b>         | 190 mm              |
| <b>PACK THICKNESS</b>     | 125 mm              |
| <b>PACK WEIGHT</b>        | 8 kg                |
| <b>LAYERS/BOX</b>         | 16                  |
| <b>M<sup>2</sup>/PACK</b> | 0.75 m <sup>2</sup> |

### Dimension pallet

|                             |                      |
|-----------------------------|----------------------|
| <b>PALLET LENGTH</b>        | 600 mm               |
| <b>PALLET WIDTH</b>         | 1000 mm              |
| <b>PALLET HEIGHT</b>        | 870 mm               |
| <b>PALLET WEIGHT</b>        | 640 kg               |
| <b>PACKS/PALLET</b>         | 80                   |
| <b>M<sup>2</sup>/PALLET</b> | 60.00 m <sup>2</sup> |

## CHARACTERISTICS

### Top layer

|                            |                           |
|----------------------------|---------------------------|
| <b>WOOD SPECIES</b>        | Oak                       |
| <b>LATIN NAME</b>          | Quercus Robur             |
| <b>GRADE</b>               | ABC                       |
| <b>CONSTRUCTION</b>        | 2-layer                   |
| <b>THICKNESS TOP LAYER</b> | 4 mm                      |
| <b>PATTERN</b>             | Hungarian point           |
| <b>CUTTING METHOD</b>      | Zaagfineer                |
| <b>BEVEL</b>               | 4 langsijden microvelling |
| <b>FINISH</b>              | Lacquer                   |
| <b>SURFACE STRUCTURE</b>   | Smooth                    |

### Composition of the support

|                                |                      |
|--------------------------------|----------------------|
| <b>SUPPORT TYPE</b>            | MPX                  |
| <b>WOOD SPECIES SUPPORT</b>    | Mixed Light Hardwood |
| <b>TOTAL THICKNESS SUPPORT</b> | 11 mm                |
| <b>ADHESION</b>                | Kruiselings          |

### Installation

|                   |                                                                                                                                  |                                      |
|-------------------|----------------------------------------------------------------------------------------------------------------------------------|--------------------------------------|
| <b>SYSTEM</b>     | <b>APPLICATIONS</b>                                                                                                              | <b>UNDERFLOOR HEATING</b>            |
| Tongue and groove | Light household use.<br>Moderate commercial use.<br>Normal commercial use.<br>Normal household use.<br>Intensive commercial use. | Yes<br><br><b>RE-SANDABLE</b><br>Yes |

### TECHNICAL SPECIFICATIONS

|                       | Norm                | Result                 |
|-----------------------|---------------------|------------------------|
| REACTION TO FIRE      | EN 13501-1          | Dfl-S1                 |
| FORMALDEHYDE EMISSION | EN 717-1            | E1                     |
| PCP                   | CEN/TR 14823        | ≤ 5ppm                 |
| THERMAL CONDUCTIVITY  | EN 12667 / ISO 8302 | 0,11m <sup>2</sup> k/w |
| BIOLOGICAL DURABILITY | EN 335              | Class 1                |
| BREAKING STRENGTH     | EN 1533             | Pass                   |
| SLIPPERINESS          | EN 15676            | Pass                   |
| MOISTURE CONTENT      | EN 13183-1          | 7% (+/-2%)             |

### CERTIFICATION



EN 14342

