

PRIME - PLANK - BRUT A14232



Dimension board	
LENGTH	2200 mm
WIDTH	180 mm
TOTAL THICKNESS	14.0 mm
THICKNESS TOP LAYER	3 mm
LAYER CONTENTS	Min 3 Pl x 2200

Dimension pack	
PACK LENGTH	2250 mm
PACK WIDTH	185 mm
PACK THICKNESS	84 mm
PACK WEIGHT	23 kg
LAYERS/BOX	6
M ² /PACK	$2.38\ m^2$

Dimension pallet	
PALLET LENGTH	2250 mm
PALLET WIDTH	950 mm
PALLET HEIGHT	1100 mm
PALLET WEIGHT	1280 kg
PACKS/PALLET	55
M ² /PALLET	130.90 m ²

CHARACTERISTICS

_	
lon	laver

WOOD SPECIES	Oak
LATIN NAME	Quercus Robur
GRADE	AB
CONSTRUCTION	2-layer
THICKNESS TOP LAYER	3 mm
PATTERN	1 strip
CUTTING METHOD	Zaagfineer
BEVEL	4 zijden 0,75 mm velling
FINISH	Onbehandeld
SURFACE STRUCTURE	Smooth

Composition of the support

SUPPORT TYPE	MPX
WOOD SPECIES SUPPORT	Berk
TOTAL THICKNESS SUPPORT	11 mm
ADHESION	Kruiselings

Installation

SYSTEM	APPLICATIONS	UNDERFLOOR HEATING
Tongue and groove	Light household use.	Yes
	Moderate commercial use.	
	Normal commercial use.	RE-SANDABLE
	Normal household use.	Yes
	Intensive commercial use.	

[©] This fact sheet was written by Labeco BVBA, Sprietestraat 326, B-8792 Waregem. Text, photographs, drawings, tables, graphs should in no way be distributed, used or copied unless LABECO BVBA has granted reproduction rights. At the moment of establishment of the sheet, all information is specified correctly. The company reserves the right to change the specifications of the product at any time without prior notice to third parties. The photographs, drawings, tables, graphs used in this sheet are intended only as illustrations. No rights can be derived from them.



PRIME - PLANK - BRUT A14232

TECHNICAL SPECIFICATIONS

	Norm	Result
REACTION TO FIRE	EN 13501-1	Dfl-S1
FORMALDEHYDE EMISSION	EN 717-1	E1
PCP	CEN/TR 14823	≤ 5ppm
THERMAL CONDUCTIVITY	EN 12667 / ISO 8302	0,11m² k/w
BIOLOGICAL DURABILITY	EN 335	Class 1
BREAKING STRENGTH	EN 1533	Pass
SLIPPERINESS	EN 15676	Pass
MOISTURE CONTENT	EN 13183-1	7% (+/-2%)

CERTIFICATION









