



### Dimension board

<b>LENGTH</b>	1900 mm
<b>WIDTH</b>	190 mm
<b>TOTAL THICKNESS</b>	10.0 mm
<b>THICKNESS TOP LAYER</b>	3 mm
<b>LAYER CONTENTS</b>	Min 6 pl 1900mm

### Dimension pack

<b>PACK LENGTH</b>	1910 mm
<b>PACK WIDTH</b>	200 mm
<b>PACK THICKNESS</b>	90 mm
<b>PACK WEIGHT</b>	21 kg
<b>LAYERS/BOX</b>	8
<b>M<sup>2</sup>/PACK</b>	2.89 m <sup>2</sup>

### Dimension pallet

<b>PALLET LENGTH</b>	1950 mm
<b>PALLET WIDTH</b>	1050 mm
<b>PALLET HEIGHT</b>	1000 mm
<b>PALLET WEIGHT</b>	1260 kg
<b>PACKS/PALLET</b>	60
<b>M<sup>2</sup>/PALLET</b>	173.40 m <sup>2</sup>

## CHARACTERISTICS

### Top layer

<b>WOOD SPECIES</b>	Oak
<b>LATIN NAME</b>	Quercus Robur
<b>GRADE</b>	CLASSIC
<b>CONSTRUCTION</b>	3-layer
<b>THICKNESS TOP LAYER</b>	3 mm
<b>PATTERN</b>	1 strip
<b>CUTTING METHOD</b>	Zaagfineer
<b>BEVEL</b>	2 zijden 0,50 mm velling
<b>FINISH</b>	Lacquer
<b>SURFACE STRUCTURE</b>	Brushed

### Composition of the support

<b>SUPPORT TYPE</b>	MPX
<b>WOOD SPECIES SUPPORT</b>	Mixed Light Hardwood
<b>TOTAL THICKNESS SUPPORT</b>	7 mm
<b>ADHESION</b>	Kruiselings

### Installation

SYSTEM	APPLICATIONS	UNDERFLOOR HEATING
Tongue and groove	Light household use. Moderate commercial use. Normal commercial use. Normal household use. Intensive commercial use.	Yes  <b>RE-SANDABLE</b> Yes

### TECHNICAL SPECIFICATIONS

	Norm	Result
REACTION TO FIRE	EN 13501-1	Dfl-S1
FORMALDEHYDE EMISSION	EN 717-1	E1
PCP	CEN/TR 14823	≤ 5ppm
THERMAL CONDUCTIVITY	EN 12667 / ISO 8302	0,11m <sup>2</sup> k/w
BIOLOGICAL DURABILITY	EN 335	Class 1
BREAKING STRENGTH	EN 1533	Pass
SLIPPERINESS	EN 15676	Pass
MOISTURE CONTENT	EN 13183-1	7% (+/-2%)

### CERTIFICATION



EN 14342

