

CLASSIC A - CHARENTES - UV LACQUER V13856



LENGTH	1900 mm
WIDTH	150 mm

Dimension board

LAYER CONTENTS

TOTAL THICKNESS 12.0 mm

THICKNESS TOP
LAYER

Min 6 Pl x 1900

Dimension pack

PACK LENGTH	1910 mm
PACK WIDTH	160 mm
PACK THICKNESS	100 mm
PACK WEIGHT	18 kg
LAYERS/BOX	8
M ² /PACK	2.28 m ²

Dimension pallet

PALLET LENGTH	1930 mm
PALLET WIDTH	1000 mm
PALLET HEIGHT	1080 mm
PALLET WEIGHT	1260 kg
PACKS/PALLET	54
M ² /PALLET	123.12 m ²

CHARACTERISTICS

Top layer

WOOD SPECIES	Oak	
LATIN NAME	Quercus Robur	
GRADE	CLASSIC A	
CONSTRUCTION	3-layer	
THICKNESS TOP LAYER	3 mm	
PATTERN	1 strip	
CUTTING METHOD	Zaagfineer	
BEVEL	Micro bevel 2 long sides	
FINISH	Lacquer	
SURFACE STRUCTURE	Brushed	

Composition of the support

SUPPORT TYPE	MPX
WOOD SPECIES SUPPORT	Mixed Light Hardwood
TOTAL THICKNESS SUPPORT	9 mm
ADHESION	Kruiselings

Installation

SYSTEM
APPLICATIONS
UNDERFLOOR HEATING

Yes

Moderate commercial use.
Normal commercial use.
Normal household use.
Yes

RE-SANDABLE
Yes

Intensive commercial use.

© This fact sheet was written by Labeco BVBA, Sprietestraat 326, B-8792 Waregem. Text, photographs, drawings, tables, graphs should in no way be distributed, used or copied unless LABECO BVBA has granted reproduction rights. At the moment of establishment of the sheet, all information is specified correctly. The company reserves the right to change the specifications of the product at any time without prior notice to third parties. The photographs, drawings, tables, graphs used in this sheet are intended only as illustrations. No rights can be derived from them.



CLASSIC A - CHARENTES - UV LACQUER V13856

TECHNICAL SPECIFICATIONS

	Norm	Result
REACTION TO FIRE	EN 13501-1	Dfl-S1
FORMALDEHYDE EMISSION	EN 717-1	E1
PCP	CEN/TR 14823	≤ 5ppm
THERMAL CONDUCTIVITY	EN 12667 / ISO 8302	0,11m² k/w
BIOLOGICAL DURABILITY	EN 335	Class 1
BREAKING STRENGTH	EN 1533	Pass
SLIPPERINESS	EN 15676	Pass
MOISTURE CONTENT	EN 13183-1	7% (+/-2%)

CERTIFICATION









