



## Dimension board

<b>LENGTH</b>	1900 mm
<b>WIDTH</b>	190 mm
<b>TOTAL THICKNESS</b>	14.0 mm
<b>THICKNESS TOP LAYER</b>	3 mm
<b>LAYER CONTENTS</b>	Min 4 Pl x 1900 mm

## Dimension pack

<b>PACK LENGTH</b>	1950 mm
<b>PACK WIDTH</b>	195 mm
<b>PACK THICKNESS</b>	115 mm
<b>PACK WEIGHT</b>	21 kg
<b>LAYERS/BOX</b>	6
<b>M<sup>2</sup>/PACK</b>	2.17 m <sup>2</sup>

## Dimension pallet

<b>PALLET LENGTH</b>	1950 mm
<b>PALLET WIDTH</b>	1150 mm
<b>PALLET HEIGHT</b>	1080 mm
<b>PALLET WEIGHT</b>	1020 kg
<b>PACKS/PALLET</b>	50
<b>M<sup>2</sup>/PALLET</b>	108.50 m <sup>2</sup>

## CHARACTERISTICS

## Top layer

<b>WOOD SPECIES</b>	Oak
<b>LATIN NAME</b>	Quercus Robur
<b>GRADE</b>	ABC
<b>CONSTRUCTION</b>	2-layer
<b>THICKNESS TOP LAYER</b>	3 mm
<b>PATTERN</b>	1 strip
<b>CUTTING METHOD</b>	Zaagfineer
<b>BEVEL</b>	Bevel 2 long sides 0,75 mm
<b>FINISH</b>	Lacquer
<b>SURFACE STRUCTURE</b>	Brushed

## Composition of the support

<b>SUPPORT TYPE</b>	MPX
<b>WOOD SPECIES SUPPORT</b>	Mixed Light Hardwood
<b>TOTAL THICKNESS SUPPORT</b>	11 mm
<b>ADHESION</b>	Kruiselings

## Installation

<b>SYSTEM</b>	<b>APPLICATIONS</b>	<b>UNDERFLOOR HEATING</b>
Tongue and groove	Light household use. Moderate commercial use. Normal commercial use. Normal household use. Intensive commercial use.	Yes
		<b>RE-SANDABLE</b>
		No

**TECHNICAL SPECIFICATIONS**

	Norm	Result
REACTION TO FIRE	EN 13501-1	Dfl-S1
FORMALDEHYDE EMISSION	EN 717-1	E1
PCP	CEN/TR 14823	≤ 5ppm
THERMAL CONDUCTIVITY	EN 12667 / ISO 8302	0,11m <sup>2</sup> k/w
BIOLOGICAL DURABILITY	EN 335	Class 1
BREAKING STRENGTH	EN 1533	Pass
SLIPPERINESS	EN 15676	Pass
MOISTURE CONTENT	EN 13183-1	7% (+/-2%)

**CERTIFICATION**



EN 14342

