# ABC - INVISIBLE - UV LACQUER - CHEVRON
**V17218**




### Dimension board

| | |
|---|---|
| **LENGTH** | 530 mm |
| **WIDTH** | 90 mm |
| **TOTAL THICKNESS** | 15.0 mm |
| **THICKNESS TOP LAYER** | 4 mm |

### Dimension pack

| | |
|---|---|
| **PACK LENGTH** | 590 mm |
| **PACK WIDTH** | 190 mm |
| **PACK THICKNESS** | 125 mm |
| **PACK WEIGHT** | 8 kg |
| **LAYERS/BOX** | 16 |
| **M²/PACK** | 0.76 m² |

### Dimension pallet

| | |
|---|---|
| **PALLET LENGTH** | 560 mm |
| **PALLET WIDTH** | 1000 mm |
| **PALLET HEIGHT** | 870 mm |
| **PALLET WEIGHT** | 640 kg |
| **PACKS/PALLET** | 80 |
| **M²/PALLET** | 60.80 m² |

## CHARACTERISTICS

### Top layer

| | |
|---|---|
| **WOOD SPECIES** | Oak |
| **LATIN NAME** | Quercus Robur |
| **GRADE** | ABC |
| **CONSTRUCTION** | 2-laags |
| **THICKNESS TOP LAYER** | 4 mm |
| **PATTERN** | Hungarian point |
| **CUTTING METHOD** | Sawn veneer |
| **BEVEL** | Micro bevel 4 sides |
| **FINISH** | Lacquer |
| **SURFACE STRUCTURE** | Brushed |

### Composition of the support

| | |
|---|---|
| **SUPPORT TYPE** | Plywood |
| **TOTAL THICKNESS SUPPORT** | 11 mm |

### Installation

**SYSTEM**

Tongue and groove

**APPLICATIONS**

Light household use.
Moderate commercial use.
Normal commercial use.
Normal household use.
Intensive commercial use.

**UNDERFLOOR HEATING**

Yes

**RE-SANDABLE**

Yes

© This fact sheet was written by Labeco BVBA, Sprietestraat 326, B-8792 Waregem. Text, photographs, drawings, tables , graphs should in no way be distributed , used or copied unless LABECO BVBA has granted reproduction rights. At the moment of establishment of the sheet, all information is specified correctly. The company reserves the right to change the specifications of the product at any time without prior notice to third parties. The photographs, drawings, tables , graphs used in this sheet are intended only as illustrations. No rights can be derived from them.

# ABC - INVISIBLE - UV LACQUER - CHEVRON
**V17218**

## TECHNICAL SPECIFICATIONS

| | Norm | Result |
|---|---|---|
| **REACTION TO FIRE** | EN 13501-1 | Dfl-S1 |
| **FORMALDEHYDE EMISSION** | EN 717-1 | E1 |
| **PCP** | CEN/TR 14823 | ≤ 5ppm |
| **THERMAL CONDUCTIVITY** | EN 12667 / ISO 8302 | 0,11m² k/w |
| **BIOLOGICAL DURABILITY** | EN 335 | Class 1 |
| **BREAKING STRENGTH** | EN 1533 | Pass |
| **SLIPPERINESS** | EN 15676 | Pass |
| **MOISTURE CONTENT** | EN 13183-1 | 7% (+/-2%) |

## CERTIFICATION

EN 14342

© This fact sheet was written by Labeco BVBA, Sprietestraat 326, B-8792 Waregem. Text, photographs, drawings, tables , graphs should in no way be distributed , used or copied unless LABECO BVBA has granted reproduction rights. At the moment of establishment of the sheet, all information is specified correctly. The company reserves the right to change the specifications of the product at any time without prior notice to third parties. The photographs, drawings, tables , graphs used in this sheet are intended only as illustrations. No rights can be derived from them.