ABC - NATURAL - UV LACQUER - HERRINGBONE
V17279

Dimension board

LENGTH	500 mm
WIDTH	90 mm
TOTAL THICKNESS	14.0 mm
THICKNESS TOP LAYER	3 mm

Dimension pack

PACK LENGTH	510 mm
PACK WIDTH	183 mm
PACK THICKNESS	125 mm
PACK WEIGHT	9 kg
LAYERS/BOX	16
M²/PACK	0.72 m^2

Dimension pallet

PALLET LENGTH	1050 mm
PALLET WIDTH	1000 mm
PALLET HEIGHT	950 mm
PALLET WEIGHT	850 kg
PACKS/PALLET	80
M²/PALLET	57.60 m^2

CHARACTERISTICS

Top layer

WOOD SPECIES	Oak
LATIN NAME	Quercus Robur
GRADE	ABC
CONSTRUCTION	2-laags
THICKNESS TOP LAYER	3 mm
PATTERN	Herringbone
CUTTING METHOD	Sawn veneer
BEVEL	Micro bevel 4 sides
FINISH	Lacquer
SURFACE STRUCTURE	Brushed

Composition of the support

SUPPORT TYPE	Plywood
TOTAL THICKNESS SUPPORT	11 mm

Installation

SYSTEM

T&G

APPLICATIONS

Light household use.
Moderate commercial use.
Normal commercial use.
Normal household use.
Intensive commercial use.

UNDERFLOOR HEATING

Yes

RE-SANDABLE

Yes

© This fact sheet was written by Labeco BVBA, Sprietestraat 326, B-8792 Waregem. Text, photographs, drawings, tables , graphs should in no way be distributed , used or copied unless LABECO BVBA has granted reproduction rights. At the moment of establishment of the sheet, all information is specified correctly. The company reserves the right to change the specifications of the product at any time without prior notice to third parties. The photographs, drawings, tables , graphs used in this sheet are intended only as illustrations. No rights can be derived from them.

ABC - NATURAL - UV LACQUER - HERRINGBONE
V17279

TECHNICAL SPECIFICATIONS

	Norm	Result
REACTION TO FIRE	EN 13501-1	Dfl-S1
FORMALDEHYDE EMISSION	EN 717-1	E1
PCP	CEN/TR 14823	≤ 5ppm
THERMAL CONDUCTIVITY	EN 12667 / ISO 8302	0,11m² k/w
BIOLOGICAL DURABILITY	EN 335	Class 1
BREAKING STRENGTH	EN 1533	Pass
SLIPPERINESS	EN 15676	Pass
MOISTURE CONTENT	EN 13183-1	7% (+/-2%)

CERTIFICATION

EN 14342

© This fact sheet was written by Labeco BVBA, Sprietestraat 326, B-8792 Waregem. Text, photographs, drawings, tables , graphs should in no way be distributed , used or copied unless LABECO BVBA has granted reproduction rights. At the moment of establishment of the sheet, all information is specified correctly. The company reserves the right to change the specifications of the product at any time without prior notice to third parties. The photographs, drawings, tables , graphs used in this sheet are intended only as illustrations. No rights can be derived from them.