



**Size Board**

|                            |                      |
|----------------------------|----------------------|
| <b>LENGTH</b>              | 1900 mm              |
| <b>WIDTH</b>               | 190 mm               |
| <b>TOTAL THICKNESS</b>     | 14 mm                |
| <b>THICKNESS TOP LAYER</b> | 3 mm                 |
| <b>PLANK QUANTITY</b>      | Min. 7 Pl. x 1900 mm |

**Size Pack**

|                           |                     |
|---------------------------|---------------------|
| <b>PACK LENGTH</b>        | 1910 mm             |
| <b>PACK WIDTH</b>         | 200 mm              |
| <b>PACK THICKNESS</b>     | 120 mm              |
| <b>PACK WEIGHT</b>        | 24 kg               |
| <b>LAYERS/PACK</b>        | 8                   |
| <b>M<sup>2</sup>/PACK</b> | 2.89 m <sup>2</sup> |

**Size Pallet**

|                             |                      |
|-----------------------------|----------------------|
| <b>LENGTH PALLET</b>        | 1930 mm              |
| <b>WIDTH PALLET</b>         | 1000 mm              |
| <b>HEIGHT PALLET</b>        | 1080 mm              |
| <b>WEIGHT PALLET</b>        | 975 kg               |
| <b>PACKS/PALLET</b>         | 40                   |
| <b>M<sup>2</sup>/PALLET</b> | 115.6 m <sup>2</sup> |

**Characteristics**


**Top layer**

|                            |                          |
|----------------------------|--------------------------|
| <b>WOOD SPECIES</b>        | Oak                      |
| <b>LATIN NAME</b>          | Quercus Robur            |
| <b>GRADE</b>               | CLASSIC                  |
| <b>CONSTRUCTION</b>        | 3-layer                  |
| <b>THICKNESS TOP LAYER</b> | 3 mm                     |
| <b>STRIPS</b>              | 1 strip                  |
| <b>CUTTING METHOD</b>      | Sawn veneer              |
| <b>BEVEL</b>               | Two long sides (0,75 mm) |
| <b>COLOUR FINISH</b>       | Natural oiled            |
| <b>SURFACE STRUCTURE</b>   | Smooth                   |

**Composition of the support**

|                                |                             |
|--------------------------------|-----------------------------|
| <b>SUPPORT TYPE</b>            | Poplar support and backing  |
| <b>WOOD SPECIES SUPPORT</b>    | Poplar                      |
| <b>SUPPORT CONSTRUCTION</b>    | 2-layer (Support, balancer) |
| <b>TOTAL THICKNESS SUPPORT</b> | 11 mm                       |
| <b>ADHESION</b>                | Crosswise (Casco)           |

**Installation**

|   |                          |                           |
|---|--------------------------|---------------------------|
| <b>SYSTEM</b>   | <b>APPLICATIONS</b>      | <b>UNDERFLOOR HEATING</b> |
| Tongue and groove system  | Light household use      | Yes                       |
|  | Moderate commercial use  | <b>RESANDABLE</b>         |
|   | Normal commercial use    | Resandable                |
|   | Normal household use     |                           |
|   | Intensive commercial use |                           |

**Certification**

This product conforms to CE standard EN 14342:2005 + A1: 2008 - Level 4 for flooring type BS EN 13489:2002 (Wood and parquet flooring, Multilayer parquet)

- Formaldehyde emission, determined according to standard EN 13183-1: E1
- Moisture content, determined according to standard EN 13183-1: 10% (+ / -2%). Fits in dry areas with a moisture content of 50% to 60%
- Width Shrinkage, complies with standard EN 13647
- Reaction to fire, determined according to standard EN 13501-1: Dfl-S1
- Does not contain any PCP (pentachlorophenol)

**Technical specifications**

- Hardness: N / mm<sup>2</sup> (Birrell Hardness) 3.40
- Thermal conductivity:  $\lambda$  14, 00 (W / (mk)) R = 0.11 m<sup>2</sup> K / W

Additional tests:

- Tested for delamination and stability according to standard EN1910 (cf. 15-189-BRUT CLASSIC)
- The bonding was tested according to EN311 standard (see 15-189-BRUT CLASSIC)