Rigid FLOORS
—DRYBACK
by lalegno

TECHNICAL DATA SHEET

FLOOR - 2.5/0.55 - 184 - DRYBACK - BARBARESCO

SKU: A16697

	STANDARD	RESULT
Dimensions and basic data		
SIZE	EN ISO 24342	Plank: 184 x 1219 mm
THICKNESS	EN ISO 24346	2.5 mm
WEAR LAYER	EN ISO 24340	0.55 mm
INSTALLATION		Dryback - glue down
SURFACE TREATMENT		PU coating + protected with aluminium oxide (anti-scratch) and stain resistant technology.
Technical data - CE EN 14041		
BEVELLED EDGE	MICRO	4 Sides
MASS/ UNIT AREA	ISO 23997	3.55 kg/m²
STANDARDS	EN ISO 10582	
CLASSIFICATION	EN 685 / EN ISO 10874 - Commercial	33: Commercial heavy
	EN 685 / EN ISO 10874 - Domestic	23: Domestic heavy
REACTION TO FIRE	EN 13501-1	Bfl-S1
STAINING RESISTANCE	EN 438-2	Pass
LIGHT FASTNESS	EN ISO 105-B02	≥6
DIMENSIONAL STABILITY	EN 434 / EN ISO 23999	≤ 0.15 %
CURLING RESULTANT TO HEAT	ISO 23999	≤ 1.5 mm
ELECTRICAL PROPERTIES	EN 1815	Pass
INDENTATION - RESIDUAL	ISO 24343-1	≤ 0.10 mm
CASTOR CHAIR	ISO 4918	Pass
THERMAL CONDUCTIVITY	EN 12667	0.02 (m²k/W)
SLIP RESISTANCE*	EN 13893 / DIN 51130	DS R10
WEAR RESISTANCE	EN 660-2 / EN 649	Class T
IMPACT RESISTANCE	EN 13329	Pass
FLOOR HEATING	Appropriate for standard heating systems in cement flooring.	Not appropriate for electric heating films.
Dangerous substances		
VOC EMISSION	French/Belgian/German Regulations	Pass
FORMALDEHYDE EMISSION	EN 717-1	E1
REACH		Friendly reach compliant
PCP	EN 12673	Pass

*Slip resistance is measured on ex-factory product. Slip resistance can be affected by surface contamination, use and how the product is maintained.

info@rigidfloors.be - www.rigidfloors.be

Rigid
—FLOORS
by lalegno